

Aluminium and aluminium alloys — Aluminium sheet, strip and plate for electrotechnical applications

The European Standard EN 14121:2003 has the status of a
British Standard

ICS 77.150.10

National foreword

This British Standard is the official English language version of EN 14121:2003.

The UK participation in its preparation was entrusted by Technical Committee NFE/35, Light metals and their alloys, to Subcommittee NFE/35/5, Wrought aluminium and aluminium alloys, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2003

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 9 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

English version

Aluminium and aluminium alloys - Aluminium sheet, strip and plate for electrotechnical applications

Aluminium et alliages d'aluminium - Tôles, bandes et tôles épaisses en aluminium pour applications électrotechniques

Aluminium und Aluminiumlegierungen - Bänder, Bleche und Platten aus Aluminium für elektrotechnische Anwendungen

This European Standard was approved by CEN on 2 January 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions.....	4
4 Ordering information	4
5 Requirements	5
5.1 Production and manufacturing processes.....	5
5.2 Quality control.....	5
5.3 Chemical composition.....	5
5.4 Mechanical properties and electrical conductivity.....	6
5.5 Freedom from defects	6
5.6 Tolerances on dimensions and form	6
5.7 Other properties.....	6
6 Test methods.....	7
6.1 Chemical composition.....	7
6.2 Tensile test	7
6.3 Electrical conductivity.....	7
6.4 Measurement of dimensions	7
6.5 Surface finish	7
6.6 Other tests	7
7 Inspection documents.....	7
8 Marking of products	8
9 Packing	8
10 Arbitration.....	8
Bibliography	9

Foreword

This document (EN 14121:2003) has been prepared by Technical Committee CEN/TC 132, "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2003, and conflicting national standards shall be withdrawn at the latest by October 2003.

Within its programme of work, CEN/TC 132 has entrusted CEN/TC 132/WG 7 "*Sheet, strip and plate*" to prepare the following standard:

EN 14121, *Aluminium and aluminium alloys — Aluminium sheet, strip and plate for electrotechnical applications.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the technical conditions for inspection and delivery, the mechanical properties and electrical conductivity of wrought aluminium sheet, strip and plate for electrotechnical applications such as bus bars and other conductors, products requiring a certain minimum electrical conductivity.

It applies to products with a thickness over 0,20 mm up to and including 150 mm.

NOTE Some of the products listed in the present standard can be subject to patent or patent applications, and their listing herein does not in anyway imply the granting of a licence under such patent right.

CEN/TC 132 affirms it's policy that in the case when a patentee refuses to grant licenses on standardised standard products under reasonable and not discriminatory conditions, then this product shall be removed from the corresponding standard.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references, the latest edition of the publication referred to applies (including amendments).

EN 485-3, *Aluminium and aluminium alloys — Sheet, strip and plate — Part 3: Tolerances on shape and dimensions for hot-rolled products.*

EN 485-4, *Aluminium and aluminium alloys — Sheet, strip and plate — Part 4: Tolerances on shape and dimensions for cold-rolled products.*

EN 515, *Aluminium and aluminium alloys — Wrought products — Temper designations.*

EN 573-3, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 3: Chemical composition.*

EN 10002-1, *Metallic materials — Tensile testing — Part 1: Method of test at ambient temperature.*

EN 10204, *Metallic products — Types of inspection documents.*

EN 12258-1:1998, *Aluminium and aluminium alloys — Terms and definitions — Part 1: General terms.*

3 Terms and definitions

For the purposes of this European Standard the terms and definitions given in EN 12258-1:1998 apply.

4 Ordering information

The ordering information shall define the product required and shall contain the following information:

- a) the form and type of product:
 - the form of the product (sheet, strip or plate);
 - the designation of the aluminium;
- b) the temper of the material for delivery according to EN 515 and, if different, the temper for use;

- c) the number of this European Standard;
- d) the dimensions and form of the product:
 - thickness,
 - width,
 - length (in the rolling direction);
- e) tolerances on the dimensions and form, in accordance with EN 485-3 or EN 485-4;
- f) quantity:
 - mass or number of pieces,
 - quantity tolerances, if required;
- g) any requirements for inspection documents;
- h) any special requirements agreed between manufacturer and purchaser. If codified product designations are used, they should be in accordance with prEN 573-5.

5 Requirements

5.1 Production and manufacturing processes

Unless otherwise specified in the order, the production and manufacturing processes shall be left to the discretion of the manufacturer.

5.2 Quality control

The manufacturer shall be responsible for the performance of all inspection and tests required by this standard prior to shipment of the product.

If purchasers wish to inspect the product at the manufacturer's works, they shall notify the manufacturer at the time of ordering.

5.3 Chemical composition

The chemical composition of EN AW-1350A and EN AW-1350 shall comply with the requirements as specified in EN 573-3.

5.4 Mechanical properties and electrical conductivity

The mechanical properties and electrical conductivity shall be in conformity with those specified in Table 1.

Table 1 — Mechanical properties and electrical conductivity

Material, temper	Specified thickness		Mechanical properties						Electrical conductivity
			Tensile strength		0,2 % proof stress	Elongation		Brinell hardness	
	mm over up to	R_m MPa min. max.	$R_{p0,2}$ MPa min.	$A_{50\text{ mm}}$ % min.		A % min.	HBW ^a approx.	20 °C MS/m min.	
EN AW-1350A-F EN AW-1350-F	≥ 2,5	150	65 ^a	—	—	—	—	—	34,5
EN AW-1350A-O EN AW-1350-O EN AW-1350A-H111 EN AW-1350-H111	0,2 0,5 1,5 3,0 6,0 12,5	0,5 1,5 3,0 6,0 12,5 20	65 65 65 65 65 65	105 105 105 105 105 105	20 20 20 20 20 20	20 22 26 29 35 —	— — — — — 32	20 20 20 20 20 20	35,4
EN AW-1350A-H19 EN AW-1350-H19	0,2	3,0	150	—	130	1	—	45	34,5
EN AW-1350A-H24 EN AW-1350-H24	0,2 0,5 1,5 3,0	0,5 1,5 3,0 12,5	105 105 105 105	150 150 150 150	75 75 75 75	3 3 5 8	— — — —	33 33 33 33	34,5
EN AW-1350A-H26 EN AW-1350-H26	0,2 0,5 1,5	0,5 1,5 4,0	120 120 120	165 165 165	90 90 90	2 3 4	— — —	38 38 38	34,5
EN AW-1350A-H28 EN AW-1350-H28	0,2 1,5	1,5 3,0	140 140	— —	110 110	2 3	— —	41 41	34,0

^a For information only.

^a For information only.

5.5 Freedom from defects

The product shall be free from defects prejudicial to its suitable and proper use.

It shall have a smooth and clean surface. However, small surface defects such as light scratches, indentations, laminations, stripes, roll marks, discoloration's and non-uniform surface appearance resulting from heat treatment, etc., which cannot always be totally avoided, are generally permitted on both sides of the product.

Whilst an operation designed to mask a fault is not permitted, the elimination of a superficial fault is permissible, provided that the dimensional tolerances and material properties continue to meet the specifications.

5.6 Tolerances on dimensions and form

The tolerances on dimensions and form shall be in conformity with EN 485-3 or EN 485-4. Other tolerances on dimensions and form shall be agreed between manufacturer and purchaser.

5.7 Other properties

Additional requirements for properties such as hardness, bending ability etc., shall be agreed between manufacturer and purchaser.

6 Test methods

6.1 Chemical composition

The methods of analysis shall be at the discretion of the manufacturer. In case of dispute concerning the chemical composition, a referee analysis shall be carried out by methods agreed between manufacturer and purchaser. The results obtained by these methods shall be accepted.

6.2 Tensile test

The tensile test shall be carried out in accordance with EN 10002-1.

6.3 Electrical conductivity

The determination of electrical conductivity shall be carried out in accordance with a documented procedure giving details, such as a temperature between 15 °C and 25 °C. This procedure shall address the precision of the measurements and possible errors.

Induction methods can be used for measurement of electrical conductivity, according to EN 2004-1, but for thin products, care shall be taken to avoid inaccuracy due to the penetration depth of the electrical field.

6.4 Measurement of dimensions

The dimensions shall be measured by means of measuring instruments which are of an accuracy consistent with that of dimensions and the dimensional tolerances.

All dimensions shall be checked at the ambient temperature in the workshop or laboratory, and, in case of dispute, at a temperature between 15 °C and 25 °C.

6.5 Surface finish

Unless otherwise specified, examination of surface finish shall be carried out without the assistance of magnifying apparatus on products before delivery.

6.6 Other tests

If other mechanical or physical tests are required, these shall be agreed between manufacturer and purchaser. These tests shall be carried out either in accordance with the existing European Standards or agreed upon by manufacturer and purchaser. The following standards may be used as guidelines:

- the Brinell hardness (HBW) in accordance with EN ISO 6506-1;
- erichsen test: in accordance with ISO 8490;
- earing test: in accordance with EN 1669.

7 Inspection documents

When requested by the purchaser and agreed by the manufacturer, the manufacturer shall provide the appropriate inspection document in accordance with EN 10204.

8 Marking of products

Marking of products shall be undertaken when agreed between manufacturer and purchaser and stated on the order. This marking shall not adversely affect the final use of the product.

9 Packing

Unless otherwise specified in European Standards relating to special products or specified in the order, the method of packing shall be determined by the manufacturer who shall take all suitable precautions to ensure that, under the usual conditions of transportation, the products will be delivered in a condition suitable for use.

10 Arbitration

In cases of dispute concerning conformity with the requirements of this European Standard and before any decision is made to reject the products, testing and examination shall be carried out by an arbitrator chosen by mutual agreement between manufacturer and purchaser.

The arbitrator's decision shall be final.

Bibliography

EN 485-1, *Aluminium and aluminium alloys — Sheet, strip and plate — Part 1: Technical conditions for inspection and delivery.*

prEN 573-5, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 5: Codification of standardized wrought products.*

EN 1669, *Aluminium and aluminium alloys — Test methods — Earing test for sheet and strip.*

EN 2004-1, *Aerospace series — Test methods for aluminium and aluminium alloy products — Part 1: Determination of electrical conductivity of wrought aluminium alloys.*

EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1:1999).*

ISO 8490, *Metallic materials — Sheet and strip — Modified Erichsen cupping test.*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.